

# White Rose

A light cream pearl background is dotted with taupe & bordeaux highlights. This granite's durability make it a neutral palette for your most discerning client.




PRICE GROUP 5

## PHYSICAL TEST RESULTS

		Imperial	Metric
Absorption by weight	ASTM C97	0.256%	0.256%
Density	ASTM C97	164.4 lb/ft <sup>3</sup>	2 633.44 kg/m <sup>3</sup>
Compressive strength	ASTM C170	34 027 Psi	234.61 MPa
Flexural strength	ASTM C880	2 495 Psi	14.9 MPa
Modulus of rupture	ASTM C99	1 937 Psi	13.36 MPa



15167 Business Ave  
Addison, TX 75001  
(972) 606-9667 office  
(972) 735-0934 fax  
info@republicelite.com

 /republicelitemultifamilyinteriors  
 /company/republicelite  
 /republicelitemf

Natural stone products inherently lack uniformity & are subject to variation in aesthetics – color, shade, finish, etc. and performance – hardness, strength. When & where your stone is quarried will affect color. Check local building codes prior to specification & installation to verify that the product technical characteristics comply with required parameters. Final selection should be made from sample submittals. The existence & dimensions of bevel may vary from lot to lot. WARNING: This product can expose you to chemicals known by the State Of California to cause cancer, including crystalline silica (airborne particles of respirable size) in dust created if the product is dry cut/ground/polished or pulverized during fabrication/installation/removal. For more info go to P65warnings.ca.gov